





980 nm Resonant Gold Nanoshells, PVP, NanoXact™

Lot Number: ECP1597


Total Diameter (TEM):	239 ± 11 nm	Mass Concentration (Au):	1.05 mg/mL
Coefficient of Variation:	4.7 %	Hydrodynamic Diameter:	282 nm
Core Diameter (TEM):	198 ± 10 nm	Zeta Potential:	-37 mV
Shell Thickness (Calc'd):	20 nm	pH of Solution:	5.7
Surface Area (Calc'd):	2.6 m ² /g	Particle Surface:	PVP
Particle Concentration:	1.8E+10 particles/mL	Solvent:	Milli-Q Water



Size Distribution



Optical Properties



Characterization Instrumentation

Diameter and Size Statistics:	JEOL 1010 Transmission Electron Microscope
Mass Concentration:	Thermo Fisher X Series 2 ICP-MS
Spectral Properties:	Agilent 8453 UV-Visible Spectrometer
Hydrodynamic Diameter/Zeta Potential:	Malvern Zetasizer Nano ZS.

Shake vigorously before use. Bath sonicate if needed. Storage: 2-8 °C. DO NOT FREEZE.

Produced under license to United States patent numbers 6,344,272, 6,685,986, and 7,371,457.

These nanoComposix products are to be used for research purposes only and are not to be used for any commercial purposes.