60 nm Silver Nanospheres, Lipoic Acid, NanoXact™

Lot Number: HKE0056

Diameter (TEM):	58 ± 4 nm	**Hydrodynamic Diameter:**	63 nm
Coefficient of Variation:	7.6 %	**Zeta Potential:**	-57 mV
Surface Area (TEM):	9.8 m^2/g	**pH of Solution:**	9.4
Mass Concentration (Ag):	0.022 mg/mL	**Silver Purity:**	99.99 %
Particle Concentration:	2.0E+10 particles/mL	**Particle Surface:**	Lipoic Acid
		Solvent:	0.2mM Potassium Carbonate







Size Distribution



Optical Properties



Characterization Instrumentation

Diameter and Size Statistics:	JEOL 1010 Transmission Electron Microscope
Mass Concentration:	Thermo Fisher X Series 2 ICP-MS
Spectral Properties:	Agilent 8453 UV-Visible Spectrometer
Hydrodynamic Diameter/Zeta Potential:	Malvern Zetasizer Nano ZS.

Storage: 2-8 °C away from light. DO NOT FREEZE.

nanoComposix, Inc
4878 Ronson Ct. Suite K
San Diego, CA 92111

nanoComposix.com

info@nanocomposix.com
Phone: (858) 565-4227
Fax: (619) 330-2556